

## Water Clear Lacquer Sanding Sealer CS-2002

### General Description

A premium quality, lacquer sanding sealer formulated for use in interior wood finishing for light to natural stains. Offering fast drying and build along with excellent sanding properties.

### Physical Properties

Vehicle Type	Coconut oil plasticized nitrocellulose
Solids by Volume	19.90 (+/-1%)
Solids by Weight	27.27 (+/-1%)
VOC	Less than 275 g/l
Flash Point	0°F
Specific Gravity	.92
Viscosity	55-60 sec. Zahn #2

### Application

Application Method	May be sprayed with conventional, airless and air assisted-airless.
Mixing Instructions	Ready to spray. May be reduced as needed with Acetone, retarder or preferred lacquer thinner.
Substrate Preparation	The surface must be clean, dry and free of grease, oil, dirt, fingerprints and any other contamination to ensure proper adhesion. Remove any loose or peeling paint. Sand basecoat with 320-400 grit sandpaper. May be applied over acrylic, nitrocellulose and UV Basecoat. Test for adhesion and compatibility before full scale application.
Application Instructions	Mix well using a power agitator prior to application. On application, the temperature of the product, substrate and coating should be above 50°F. Apply up to 3 coats, allowing sufficient drying time between coats.
Coverage	Approx. 285 square feet per gallon at 1 dry mil. @ 100% transfer efficiency. Actual coverage may vary depending on application technique, equipment, and weather conditions.

### Curing / Drying Time Properties

Air Drying Time (77°F, 50% Humidity)	
Dust Free	10-15 min.
Sand	20-25 min.
Package	4-6 hours

### Force Dry Time

Flash-Off	10 min.
No more than 120°F	20-30 min.
Package in 2-4 hours	

### Features / Advantages

- Fast Build
- Fast Drying
- Sands Easily

### Recommended For

- General Purpose Interior
- Interior Doors
- Kitchen Cabinets
- Interior Shutters & Moldings

### Safety / Clean Up

Please read the product Safety Data Sheet and product label before using product. Applications tools must be cleaned with acetone after use. Dispose of any leftover materials in accordance with local, state, or federal regulations.



CIC COATINGS | 2935 Almeta Lane | McKinney, TX 75069 | Ph: 972-384-1280 |

[www.ciccoatings.com](http://www.ciccoatings.com)

We warrant our products to be of good quality and will replace or, at our discretion, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, CIC Coatings, LLC MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. The information provided herein is based on technical data that is believed to be reliable. CIC Coatings, LLC makes no representation or warranty as to the completeness or accuracy thereof and assumes no liability resulting from its use for any claims, losses, or damages of any third party and shall have no other liability with respect thereto.